

## VARIO DB Sealing Tape

Parameter	Typical performance values		
<b>Application/Intended use</b>			
	For producing an airtight bond between <b>ISOVER VARIO KM</b> and <b>VARIO KM Duplex UV</b> climate membranes and building components such as gable walls, partition walls, centre purlins, jamb walls, floors, etc.		
<b>Material/Specification</b>			
<b>Material</b>	Flexible polyurethane foam impregnated with a high-quality, acrylic-based, permanently tacky plastic.		
<b>Consistency</b>	Paste-like and elastic.		
<b>Contents/ Packaging</b>	<b>Width</b> mm	<b>Length</b> m	<b>Rolls / Pack</b> Pieces
	17	8	6
<b>Technical performance</b>			
<b>Curing speed</b>	Approx. 2 mm/h / 24 h at 23°C and 50 % relative air humidity, in accordance with DIN 50014		
<b>Tensile strength</b>	≥ 0.11 N/mm <sup>2</sup> in accordance with DIN 53504.		
<b>Resistance to wood preservatives</b>	Resistant to water- and oil-based wood preservatives in accordance with DIN 52168.		
<b>Resistance to ageing</b>	Permanently elastic.		
<b>Shelf life</b>	24 months at a storage temperature of + 5°C to + 40 °C.		
<b>Temperature range</b>	- 40°C to + 100°C.		
<b>Site information</b>			
<b>Application temperature</b>	- 5°C to + 50°C.		

The information given in this Technical Data Sheet is correct to the best of our knowledge and experience at the time of publication. If not expressly agreed otherwise, this information does not represent a warranty in the legal sense of the word. As the state of our knowledge and experience is constantly changing, the information in this data sheet is subject to revision. We therefore kindly ask you to always use the latest issue of this Technical Data Sheet.

The product applications described in this data sheet cannot take the special circumstances of individual cases into account. Therefore carry out sufficient tests to ensure our products are suitable for the intended application. Please contact our ISOVER Technical Team if you have any questions.

All sales are based on our General Terms and Conditions.